

Oscine 01-Crystal



BASIC INFORMATION

| | | | |
|---------------------------|----------------------------|-------------------------------|------------------------|
| Launch Date | 201904 | Delivery Time Special Lab Dip | 3 |
| Country of Origin | Turkey | Roll Diameter in CM | 0.00 |
| Roll Diameter in INCH | 0.00 | Use for Drapery or Curtains | Yes |
| Use for IMO Marine | Yes | Characteristic | SHEER |
| Composition | 100% Polyester inherent FR | Repeats | V:20.00 cm H: 24.00 cm |
| Width CM | 300.00 | Width INCH | 118.11 |
| Weight GSM | 80 | Martindale | |
| Wyzenbeek | 5 | Horizontal Repeat in CM | 24.00 |
| Horizontal Repeat in INCH | 9.45 | Vertical Repeat in CM | 20.00 |
| Vertical Repeat in INCH | 7.87 | Average Piece Length in M | 50 |

CATEGORY

Colouring Type 0000000002

Care codes

| | | | |
|-----------|--|------------|---------------------|
| Iron | Low iron at max 110°C | Bleach | Do not bleach |
| Dry Clean | Dry-cleaning in perchloroethylene gentle cycle | Tumble Dry | Mild drying process |

FABRIC TYPE

| | | | |
|---------------------|--------|--------------------|--------|
| Useable Width CM | 300.00 | Useable Width INCH | 118.11 |
| Average Yarn Number | 125.00 | Weight GSM | 80 |

SPECIFICATIONS

| | | | |
|--|-------|--|-------|
| Acoustic absorption | E/NA | Martindale rubs | |
| Wyzenbeek double rubs | 5 | Shrinkage warp after washing at 40 degrees Celsius | 0.33- |
| Shrinkage weft after washing at 40 degrees Celsius | 0.20- | | |

Colour Fastness to Light ISO 105 B02

| | | | |
|--------------------------|---|--|--|
| Colour Fastness to Light | 6 | | |
|--------------------------|---|--|--|

Colour Fastness to Water ISO 105 E01

| | | | |
|--------------------------|---|--|--|
| Colour Fastness to Water | 5 | | |
|--------------------------|---|--|--|

Tearing Strength ISO 13937 3

| | | | |
|-------------------------|----|--|--|
| Tearing Strength Warp N | 22 | | |
|-------------------------|----|--|--|

Elongation ISO 13934 1

| | | | |
|-----------------|----|--|--|
| Elongation Warp | 34 | | |
|-----------------|----|--|--|

Resistance to Domestic Washing 40 degrees ISO 6330

| | | | |
|-----------------------------|-------|-------------------------|-------|
| Dimensional Change Warp | 0.33- | Dimensional Change Weft | 0.20- |
| Colour Fastness ISO 105 C06 | 5 | | |

Resistance to Domestic Washing 60 degrees ISO 6330

| | | | |
|-----------------------------|-------|---------------------------------------|-------|
| Dimensional Change Warp | 0.66- | Dimensional Change Wrap after Ironing | 0.27- |
| Dimensional Change Weft | 0.20- | Dimensional Change Weft after Ironing | 0.27- |
| Colour Fastness ISO 105 C06 | 5 | | |

Resistance to Dry Cleaning P ISO 105 D01

| | | | |
|-------------------------|------|---------------------------------------|------|
| Dimensional Change Wrap | 0.00 | Dimensional Change Wrap after Ironing | 0.00 |
| Dimensional Change Weft | 0.00 | Dimensional Change Weft after Ironing | 0.00 |

Dimensional Stability ISO 3759

| | | | |
|-------------------------|------|-------------------------|-------|
| Dimensional Change Wrap | 0.00 | Dimensional Change Weft | 0.20- |
|-------------------------|------|-------------------------|-------|